

Product Data Sheet

Sarnavap 2000 E

provisional

Property	Unit	Value	Standard
Raw material		HD/LDPE	
Colour		green (opaque)	
Dimensions:			
Width	m	4.00	SIA V 280/1
Thickness	mm	0.225	
Weight	g/m ²	215	
Length of the roll	m	25	
Width of the roll	m	2.0	
Weight of the roll	kg	approx. 22.5	
Vapour diffusion resistance factor [μ]	-	1'666'667	SIA V 280/6
Air layer thickness equivalent to diffusion (S-value) δ Air = 0.72 mg/mhPa	m	400	SIA V 280/6
Tensile strength	N/mm ²	20	SIA V 280/2
Elongation at break	%	300	SIA V 280/2
Nail shank tear resistance	N	200	EN 12310-1
Temperature stability	°C	+70/-20	SIA V 280/4
Fire rating		5.2	SIA V 280/12 / VKF
Fire class		B2	DIN 4102/1



Sarnafil International AG
Industriestrasse
CH-6060 Sarnen
Switzerland
Phone +41 41 666 99 66
Fax +41 41 666 98 99
ba-roofing.sfin@sarna.com
www.sarnafil.com

All data in our product information are based on our current knowledge and experience. They do not release users from careful testing of the application and strict observation of the relevant processing regulations because of the wide range of possible influences during the application and use of our products. Legally valid assurances of specific characteristics or suitability for special purposes of application other than those provided in our documentation for the specific product cannot be inferred from our information. Any protective rights or existing laws and provisions must be followed by the recipient or processor of our products at their own responsibility. Moreover, our general terms and conditions of sale and warranty are valid.